

weberart tavan optima

Interior ceiling paint

Technical data sheet
Düzenleme: 01.02.202
Revizyon No: 001

■ Description

Akrilik based, interior ceiling paint

■ Reference standarts

- TS 5808
- G marking
- Public works Pos No: 04.524/01

■ Advantages

- Provides easy application with its high covering feature
- Allows substrate to breathe
- Odorless
- High adherence and covering decorative purposes.

■ Application areas

Used on interiors of all buildings for decorative purposes.



■ Application substrates

- Interior walls;
- Cement-based renders,
- Concrete (**webertec R**, **webertec RK**, **webertec RM** applied)
- Plaster render, gypsum block, plaster board substrates,
- Gas concrete (gas concrete render or **webertec RM** applied),
- Old painted substrates,
- *Please consult us for all other application substrates.

■ Preparation of substrates

- Substrate should be clean, dry, smooth and sound.
- Substrates should be primed with **weberprim art** without diluting and application of **weberart tavan optima** should be started at least 6 hours later.

■ Application conditions

- Ambient temperature is between +5 °C and +30 °C.
- Avoid application in very damp and/or hot weather.

■ Application tools

Lambskin roller and brush

■ Application

- **weberart tavan optima** should be diluted with water in the rate of 30 % by volume for the first and second coat in brush and roller application, and should be mixed well until homogenous state is achieved.
- **weberart tavan optima** should be applied to the entire substrate in two coats with lambskin roller or brush roller.

■ Consumption

330-350 gr/m² (for two layers).
**This is an average value.*

■ Technical specifications

PRODUCT	weberart tavan
Chemical structure	Liquid
Application temperature	Between +5°C ile +30°C
Drying time	6-24 hours
Color	White
Density	~ 1,74 gr/cm ³
PERFORMANCE	
Web scrub resistance	Class 5
Opacity	Class 1 (4,5 m ² /l)
Grain size	Thin
Glossiness	Matt

■ Points of attention

- To avoid tonality differences, products which have the same BATCH NUMBER and PRODUCTION DATE should be used on each facade.
- Never use salty water.
- Never add lime and similar foreign materials.
- All tools used for application should be cleaned with water before drying.
- Paint and solution should be mixed as the amount planned to be used.

The stated times apply for 20°C substrate and ambient temperature; increase at lower temperatures and decrease at higher temperatures. **Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş.** is not responsible for the application errors arising from use of product beyond its intended purpose of failure to comply with the forgoing application conditions and advice on the product.

Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.
Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No:284 • 35730 Kemalpaşa • İzmir • Türkiye
Tel: +90 (232) 397 07 00 • www.tr.weber • info@weber.com.tr • Çözüm Hattı 444 6 990

weber
SAINT-GOBAIN

■ Storage

Packaging	<ul style="list-style-type: none">• 17,5 kg (10 l)• 10 kg (5,7 l)• 3,5 kg (0,6 l)
Shelf life	<ul style="list-style-type: none">• 1 year as of the production date in dry and moisture- free environment provided that packages will not be opened.• Package should be kept tightly closed when not in use. Package should be protected against frost.

■ Safety precautions

- Use appropriate safety equipment (mask, gloves, glasses).
- Protect your eyes/face.
- Avoid direct contact with eyes and skin.
- In case of contact with eyes, rinse immediately with plenty of clean water and seek medical attention.
- Please read Safety Data Sheet (SDS) for further safety information.

LEGAL DISCLAIMER

Saint-Gobain Weber Yapı Kimyasalları San. Ve Tic. A.Ş. is not responsible for any errors arising from the use of product beyond its intended purpose or not complying the application procedures mentioned above.

The stated times apply for 20°C substrate and ambient temperature; increase at lower temperatures and decrease at higher temperatures. Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose of failure to comply with the forgoing application conditions and advice on the product.